

Tryark FR Coverall

ARKFR220C

DESCRIPTION

TIL Workwear Try Ark Flame Retardant (FR) Coverall are carefully constructed with premium materials that meets or exceed safety standards and are designed for maximum comfort, durability and protection against hazardous conditions. Our 100% cotton fabrics provide the wearer with maximum comfort. Naturally soft, these fabrics offer an excellent moisture management control and are engineered to sustain extensive industrial launderings.

KEY FEATURES

- 100% Cotton
- Flame Resistant

DETAILED FEATURES

- Premium flame retardant fabric
- Reinforced stitching for durability
- Multiple pockets for storage
- Comfortable fit for ease of movement
- Durable and long-lasting materials
- Easy to clean and maintain

APPLICATIONS

- Oil & Gas Industry
- Manufacturing
- Construction
- Mining
- Logistics
- Warehousing

 **Royal Blue** Code: RYB



OTHER COLORS



Sunrise
Orange



Navy Blue



Tan Brown



Ribbon Red



Ocean Blue

PRODUCT INFORMATION

Category: Workwear

Available Sizes: 30, 32, 34, 36, 38, 40, 42, 44, 46, 48, 50, 52, 54, 56, 58, 60

| PACKAGING WASTE | | | | | | |
|-----------------|-------|------|------------|-------------|------------|-------------|
| Material | Type | Unit | Weight (g) | Length (mm) | Width (mm) | Height (mm) |
| Cardboard | Outer | 1 | 0.05 | 0.716 | 0.232 | 0.414 |
| Plastic | Inner | 1 | 0.01 | 0.5 | 0.4 | 0.0 |
| Paper | Inner | 1 | 0.002 | 0.21 | 0.148 | 0.0 |



Tryark FR Coverall

ARKFR220C

Technical Data

| Parameter | Specification | Standard / Test Method |
|--------------------|--------------------------------|------------------------|
| Product Code | ARKFR220C | |
| Width | 148 cm (+2/-1 cm) | ISO 22198:2006 |
| Weight | 220g/m ² (±5%) | ISO 3801:1977 |
| Composition | 100% Cotton | |
| Construction | Twill 3/1 S | |
| Available finishes | Durable flame-retardant finish | |








Physical Performance

| Parameter | Specification | Standard / Test Method |
|------------------|------------------------|--------------------------|
| Tensile Strength | 1000 N x 450 N (± 10%) | NEN-EN-ISO 13934-1: 2013 |
| Tear Strength | 25 N x 25 N (± 10%) | NEN-EN-ISO 13937-2: 2000 |
| pH | 4 - 7.5 | NEN-EN-ISO 3071: 2005 |


Flammability Performance

| Parameter | Specification | Standard / Test Method |
|---------------------|-------------------------------|-----------------------------------|
| After Wash and Dry | 50 Cycles | ISO 15797 procedure 8, 75 C: 2002 |
| Ignition to surface | Meets ISO 14116: 2015 index 3 | ISO 15025 Part A: 2000 |

Care Labelling

| Parameter | Specification | Standard / Test Method |
|-----------------------|---|------------------------|
| Domestic Laundering |      | |
| Industrial Laundering | 75°C | |
| PPE Requirements |  optional:  | |

Certifications

| Icon | Specification | Standard / Test Method |
|---|---|--|
|  | Industrial flame and heat hazards | EN ISO 11612:2008 A1, B1, C1, F1 (A1 + A2= 100 x ISO 15797 - 75°C) |
|  | Contrast colours: Delftblue 89249, Twilight 89250 | EN ISO 20471: 2013 |
| | General requirements*** | EN ISO 13688: 2013 |
| | Öko-Tex Standard 100, class 2 | Centexbel, no. 0903009 |



All mentioned data must be considered as indicative values. To the best of our knowledge all information contained herein is accurate. PARKER Coverall declines any form of liability related to the use of the attached specimen that shall be regarded as a sample only and therefore not meant to be used in any form of garment making.

